



Art.-No.:6.7040.1000

7040

Tyre Coat

Characteristics

4CR 7040 is a specially formulated paint to brighten up old tyres and rubber parts, as well as black letterings.

V.O.C. Value

EC limiting value for the product (cat. B/e): 840 g/l (2007)

This product contains max. 588 g/l VOC [4,9 lbs/gal]

Tech Tip

- short drying time
- high UV and weather resistance
- very high water resistance

Application

Spray gun - Air /Flowjar:

Spraying pressure: 2,2 - 2,5 bar inlet pressure

Spraying nozzle: 1,5 - 2 mm

Spraying operations: 1-2

Airless / Airmix:

Spraying pressure: 120 - 150 bar

Spraying nozzle: 0,33 mm

Spraying operations: 1-2

Drying:

Object temp. 20°C: dust dry after 15 min. / set to touch after 1 h

Technical Data

Colour shade	black
Thinners	0505 (addition approx. 10 - 15%)
Spraying viscosity 20°C	18 - 22 s 4 mm DIN
Coat thickness / dry film	30 µm
Curing time / Flash off time	10 - 15 min.
Consumption	5 - 7 m ² /l

Storage and Transportation

At least 3 years, if stored tightly closed in original containers.