



Art.-No.:6.7437.0400

7437

2K Highspeed Clearcoat Spray

Characteristics

4CR 2K Highspeed Clearcoat Spray is a fast drying, brilliant gloss clearcoat for the clear over base coating with an excellent flow. Highly resistant against all kinds of weathering, as well as chemical and mechanical load.

High UV-protection, non-yellowing, lightfast. Excellent scratch resistance. Excellent flow and surface finish. Safe and clean transfer of the hardener. Fuel resistant.

V.O.C. Value

EC limiting value for the product (cat. B/e): 840 g/l (2007)

This product contains max. 840 g/l VOC [7.01 lbs/gal]

Application

Substrate: 2-layer basecoats. Clean, free from grease and fatt, and thoroughly dry old substrates.

Pretreatment / Cleansing: Pre-cleansing with 4CR silicone remover.

Processing conditions from +10°C and up to 80% relative air humidity.

Drying Times:

Dust-dry: after approx. 10 -15 min.

Set to touch: after approx. 4 h.

Full hardness: after 24 h.

Prior to application, all substrates must be clean, dry and degreased. Before spraying, take the red button from the cap and attach to the pin on the bottom of the aerosol. Press red button with the ball of your hand until a stop is reached. Shake can vigorously for 2 minutes. Spray to test. Spraying distance approx. 25 cm. Apply 2 to 3 coats of 2K-Topcoat with approx. 3 - 5 minutes flash-off time.

Technical Data

Colour / Grade of Gloss	Colourless / High Gloss
Pot-life	6 h