Art.-No.:6.0409.2501

0409

UHS Hardener fast

Characteristics

UHS hardener 0409 is an isocyanate hardener, and is the hardener for 7255 UHS Clearcoat.

Application

Always mix well with the main Product (7255).
When used always make sure that the can has been closed properly because the hardener responds to dampness.

Drying Times with UHS Hardener fast:
-Dust free time at 20ºC: 20-30 min
-Dry to handle at 20ºC: 4 hours
-Through dry at 20ºC: 12 hours
-Through dry at 60ºC object temperature: 20 min
-Through dry at IR: 8- 15 min

Advice: Do not breathe in the mist.

Technical Data

Viscosity	ca. 18 s 4mm
Colour	colourless
Ratio	See basis product
Potlife	30- 45 min (at 20ºC)

Storage and Transportation

Storage: Keep dry an frost-protected.
At least 12 months if stored in closed original containers.

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products.

...the professional choice.